



**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar  
İstanbul/ TÜRKİYE

**TEST REPORT**  
*DENEY RAPORU*



AB-0583-T
21032109
11-21

**Customer name:** LTS TEKSTİL SAN VE TİC LTD ŞTİ.  
**Address:** ATATÜRK MAH CEMAL GÜRSEL CAD NO:6/5 KIRAÇ  
ESEN YURT/İSTANBUL

**Buyer name:** -

**Contact Person:** ALİ RIZA ALPER

**Order No:** 8692241008581 - 8692241858124  
**Article No:** ART 8581

**Name and identity of test item:** Pink plastic trainer seat(Pink)

**The date of receipt of test item:** 26.10.2021  
**Re-submitted/re-confirmation date:** 28.10.2021  
**Date of test:** 28.10.2021-03.11.2021  
**Remarks:** -

**Sampling:** The results given in this report belong to the received sample by vendor.

**End-Use:** -

**Care Label:** Not Specified

**Number of pages of the report:** 5

*The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co- The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.*

*EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.*

*The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.*

<b>Seal</b>	<b>Date</b>	<b>Customer Representative</b>	<b>Head of Testing Laboratory</b>
	04.11.2021	Zahide TAPAN	Sevim A. RAZAK
			04.11.2021

This report shall not be reproduced other than in full except with the permission of the laboratory.  
Testing reports without signature and seal are not valid

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

21032109

11-21

REQUIRED TESTS	EVALUATION	COMMENTS
<b>ECOLOGICAL TESTS</b>		
Total Lead	P	
Total Cadmium	P	
Phthalates	P	
PAH's	P	
P:Pass F: Fail R: Refer to retailer technologist Test results were evaluated according to "Registration, Evaluation, Authorisation and Restriction of Chemicals" Legislation limit values dated on 23.06.2017 and No: 30105		

**REMARK:** Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified.If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. Tests marked (\*) in this report are not included in the accreditation schedule



This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

21032109

11-21

## TEST RESULTS

<b>TOTAL LEAD CPSC-CH-E1002-08.3-2012</b>		
The amount of total lead is extracted in suitable acidic solution using with microwave technique and determined using ICP-MS.		
	<b><u>CAS NO</u></b>	<b><u>REQUIREMENT</u></b>
Total Lead (Pb)	<b>7439-92-1</b>	< 0.05 %(500 mg/kg)
<b>RESULTS</b>		
<b>SAMPLE NO/PART NO:</b>	<b>TOTAL LEAD RESULT</b>	<b>EVALUATION</b>
<b>Pink plastic trainer seat</b>	N.D. <sup>(1)</sup>	PASS

<b>CADMIUM (Cd); EN 1122-2001</b>		
The Cadmium content in sample is separated by wet-decomposition method.Amount of cadmium is determined using ICP-MS		
	<b><u>CAS NO</u></b>	<b><u>REQUIREMENT</u></b>
<b>Cadmium (Cd)</b>	<b>7440-43-9</b>	< %0.01 (100 mg/kg)

<b>RESULTS</b>		
<b>SAMPLE NO/PART NO:</b>	<b>CADMIUM(Cd) RESULT</b>	<b>EVALUATION</b>
<b>Pink plastic trainer seat</b>	N.D. <sup>(1)</sup>	PASS

N.D <sup>(1)</sup>: Not detected

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

21032109

11-21

## TEST RESULTS

### DETERMINATION OF PHTHALATES; CPSC-CH-C1001-09.4:2018

Test sample is extracted in suitable organic solvent in extraction device.

The extract is analyzed by GC-MS and result is given.

	<u>Cas No:</u>	<u>REQUIREMENT</u>
DEHP/ Di-(2-ethylhexyl) phthalate	(117-81-7)	
DBP/ Dibutylphthalate	(84-74-2)	
BBP/ Butylbenzylphthalate	(85-68-7)	
DINP/ Di-iso-nonylphthalate	(28553-12-0)/ (68515-48-0)	
DIDP/ Di-isodecylphthalate	(26761-40-0)/ (68515-49-1)	
DNOP/ Di-n-octylphthalate	(117-84-0)	
<b>Total concentration</b>		< 0.1 %

Sample	Phthalates Result	Total	EVALUATION
Pink plastic trainer seat	ND <sup>(1)</sup>	ND <sup>(1)</sup>	PASS

ND<sup>(1)</sup>: Not detected

Gen.fl136-2/03

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

21032109

11-21

## TEST RESULTS

### **POLYCYCLIC AROMATIC HYDROCARBONS(PAH); EKOTEKS 56 (REF:ZEK.01.02-8)**

Test sample is extracted with suitable solution in ultrasonic bath at 60±2°C.After clean-up he extract is analyzed using by GC-MS.

	<u>CAS NO</u>	<u>REQUIREMENT</u>
Benzo(a)anthracene (BaA)	56-55-3	< 0,5 mg/kg (%0,00005)
Benzo(a)pyrene(BaP)	50-32-8	< 0,5 mg/kg (%0,00005)
Benzo(b)fluoranthene(BbFA)	205-99-2	< 0,5 mg/kg (%0,00005)
Benzo(e)pyrene (BeP)	192-97-2	< 0,5 mg/kg (%0,00005)
Benzo(j)fluoranthene(BjFA)	205-82-3	< 0,5 mg/kg (%0,00005)
Benzo(k)fluoranthene (BkFA)	207-08-9	< 0,5 mg/kg (%0,00005)
Chrysene (CHR)	218-01-9	< 0,5 mg/kg (%0,00005)
Dibenzo(a,h)anthracene(DBAhA)	53-70-3	< 0,5 mg/kg (%0,00005)

<b>Sample</b>	<b>RESULT</b>	<b>EVALUATION</b>
<b>Pink plastic trainer seat</b>	<b>ND<sup>(1)</sup></b>	<b>Pass</b>

N.D <sup>(1)</sup>: Not detected

Gen.fl136-2/03